



# INTERIOR ACOUSTICS


# FRONTIER™ ACOUSTIC RAFT

## MANUFACTURER'S GUARANTEE

Pat. Pending NZ 727634, AU 2016273959

Frontier™ Acoustic Raft is manufactured by Autex Industries Ltd and Autex Australia Pty Ltd under an ISO 9001 certified Quality Management System. The product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all of the performance properties stated within this guarantee.

**Product Name** Frontier™ Acoustic Raft  
**Description** 100% polyester complete modular acoustic fins

AUTEX 	METRIC
Size	Length:2400mm
Thickness	12mm
Tolerance	(+/- 6%)
Weight	2300gsm

### COMPOSITION

100% Polyester Fibre from polyethylene terephthalate (PET). Made from Autex Cube™ which contains a minimum of 45% previously recycled polyester fibre.

### SUITABLE APPLICATIONS

Suspended or direct fix with patented aluminium channels and connector clips.

### COLOUR FASTNESS TO LIGHT

Frontier is suitable for indoor use only. Light fastness is dependent on use and exposure. Frontier has been evaluated to the following standard:

ISO 105-B02:2014

Rating: 6 (Highest = 7)

### FIRE RATING

Frontier is a value-added product made from Autex Cube™ as the base material. Cube™ has been evaluated using the following test methods:

ISO 9705: 1993

Classification: Group 1-S

Smoke Production Rate: <5.0m<sup>2</sup>/s

As required by NZBC C./VM2

AS ISO 9705 - 2003

Classification: Group 1

(SMOGR<sub>Arc</sub>): <100m<sup>2</sup>/s<sup>2</sup>

Assessed using methodology AS ISO 9705:2003 in accordance with AS 5637.1:2015, as required by BCA Specification C1.10-4 FI 4974 dated 16<sup>th</sup> September, 2012 and FAR 4055-2 dated 8<sup>th</sup> October, 2013

EN13501-1:2007+A1:2009

B - s2, d2

WF336911 dated 25th February 2014

ASTM E-84-15a

Class A, FS:0 - SD:45

RJ44792 dated 25th January, 2016

### ACOUSTIC PERFORMANCE

Frontier Acoustic Raft is specifically designed to reduce and control reverberating noise in building interiors.

Sound Absorption Coefficients according to ISO 354.

DESCRIPTION	University of Auckland Test report number	FREQUENCY (Hz)						
		125	250	500	1000	2000	4000	NRC
Frontier Acoustic Raft 12mm Trapezoid, 300 centres	T1905-11	0.25	0.65	0.85	1.05	1.15	1.15	0.95
Frontier Acoustic Raft 12mm Blade, 300 centres	T1905-10	0.20	0.35	0.60	1.00	1.25	1.25	0.80
Frontier Acoustic Raft 12mm Beam 100, 150 centres	T1945-4	0.05	0.25	0.55	0.95	1.15	1.20	0.75
Frontier Acoustic Raft 12mm Beam 250, 300 centres	T1945-5	0.20	0.45	0.70	1.10	1.35	1.30	0.90

### VOC EMISSIONS

Autex polyester has been tested for chemical emissions in accordance with ASTM D5116 and is considered as a low VOC product.

VOC concentration: 0.009 mg/m<sup>3</sup> (7 days)

### FINISH

Frontier Acoustic Raft does not have a pattern repeat, but it does have a directional grain. The product may vary from samples and batch to batch due to fibre blending and lay-up, which is an inherent feature of this product.

### PHYSICAL DESCRIPTION / PROPERTIES

Boiling Point:	N/A
Melting Point:	250°C   482°F
Vapour Pressure:	N/A
Specific Gravity:	Polyester 1.38
Flash point:	N/A
Explosive limits:	N/A
Solubility in water:	Not soluble
Alkalinity:	pH 7.8
Relative Vapour Density:	N/A

### CARE AND MAINTENANCE

Maintain in accordance with the Care and Maintenance Guide available for this product.